

B16

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
14 December 2000 (14.12.2000)

PCT

(10) International Publication Number  
**WO 00/74690 A1**

- |   |   |
|---|---|
| <p>(51) International Patent Classification<sup>7</sup>: A61K 33/06, 35/52</p> <p>(21) International Application Number: PCT/US00/02780</p> <p>(22) International Filing Date: 2 February 2000 (02.02.2000)</p> <p>(25) Filing Language: English</p> <p>(26) Publication Language: English</p> <p>(30) Priority Data:<br/>09/327,761 7 June 1999 (07.06.1999) US</p> <p>(71) Applicant: WRIGHT MEDICAL TECHNOLOGY, INC. [US/US]; 5677 Airline Road, Arlington, TN 38002-9501 (US).</p> <p>(72) Inventors: PETERSEN, Don; 97000 Wood Green Lane, Lakeland, TN 38002 (US). HAGGARD, Warren, O.;</p> | <p>6600 Stephan Ridge Drive, Bartlett, TN 38134 (US). RANDOLPH, Don; 1605 S. Prospect Street, Wheaton, IL 60187 (US). HAGAN, Cary; 8517 Farmington Cove, Germantown, TN 38139 (US).</p> <p>(74) Agents: LONDA, Bruce et al.; Londa and Traub LLP, 37th floor, 20 Exchange Place, New York, NY 10005 (US).</p> <p>(81) Designated States (<i>national</i>): AU, CA, JP.</p> <p>(84) Designated States (<i>regional</i>): European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).</p> <p>Published:<br/>— With international search report.</p> <p><i>For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.</i></p> |
|---|---|



WO 00/74690 A1

(54) Title: BONE GRAFT SUBSTITUTE COMPOSITION

(57) Abstract: A bone graft substitute composition comprising calcium sulfate; a mixing solution selected from the group consisting of sterile water, sodium chloride, phosphate buffered saline, potassium chloride, and sodium sulfate; and a plasticizing substance selected from the group consisting of carboxymethylcellulose, polyvinyl alcohol, methylcellulose, and hydroxypropyl methylcellulose.

## SPECIFICATION

5

## BONE GRAFT SUBSTITUTE COMPOSITION

## BACKGROUND OF THE INVENTION:

The present invention relates, in general, to bone graft substitute compositions.

10 Calcium sulfate has been clinically used for many years as a bone void filler with successful results.

Hanker et al., U.S. Patent 4,619,655, issued October 28, 1986, discloses an animal implant comprising a scaffold material composed of plaster of Paris and a non-  
15 bioresorbable calcium material (such as calcium phosphate ceramic particles) bound with the plaster of Paris; a method of inserting such a composition in fluid or semisolid form into the appropriate body location of an animal (e.g., about a fracture locus); and a method of  
20 inserting a preform of such composition into the appropriate location of an animal (e.g., at the locus of a fracture).

Gitelis, U.S. Patent 5,147,403, issued September 15, 1992, discloses a method or technique for implanting a  
25 prosthesis comprising the steps of first preparing the surface of a bone to receive the prosthesis, then applying a calcium sulfate suspension in free flowing form to the prepared bone surface, and then seating the prosthesis to the coated bone surface.

30 Randolph, U.S. Patents 5,614,206, issued March 25, 1997, and 5,807,567, issued September 15, 1998, disclose processes for preparing pellets by mixing of calcium sulfate, water and other medicaments to provide controlled

release of calcium sulfate and medicaments.

Snyder, U.S. Patent 5,425,769, issued June 20, 1995, discloses a composition for an artificial bone substitute material consisting of collagen in a calcium sulfate matrix which can be rendered porous by a foaming agent. The composition is adaptable for osseous repair by adjusting the collagen and calcium sulfate in varying ratios to suit particular applications and including admixtures of growth factors.

10       Sottosanti, U.S. Patent 5,366,507, discloses a composition for use in bone tissue regeneration, the composition containing a barrier material and a graft material. The barrier material can be calcium sulfate, while the graft material may consist of a composite graft material containing demineralized, freeze-dried, allogenic bone and calcium sulfate.

15       Sottosanti, U.S. Patent 5,569,308, discloses a method for use in bone tissue regeneration including first filling a graft site with graft material, and then placing a layer of barrier material over at least a portion of the graft material. The barrier material can be calcium sulfate, while the graft material may consist a composite graft material containing demineralized, freeze-dried, allogenic bone and calcium sulfate.

25       Hanker et al, "Setting of Composite Hydroxylapatite/Plaster Implants with Blood for Bone Reconstruction," *Proceedings of the 44th Annual Meeting of the Electron Microscopy Society of America*, Copyright 1986, discloses using blood as the only moistening agent in a plaster or plaster/HA mixture as long as accelerator salts are utilized, and suggests that the putty-like consistency of such compositions offers distinct advantages in moldability and workability.

Osteotech, Inc., of Shrewsbury, New Jersey, markets a bone graft substitute under the mark Grafton®. It is comprised of demineralized bone matrix and glycerol as a carrier material. The carrier material, glycerol, is a viscous, gel-like, weak alcohol that is hydrophilic and water soluble. It is recognized by the Food and Drug Administration as a "Generally Regarded As Safe" substance.

DePuy, Inc., of Warsaw, Indiana, markets a bone graft substitute under the mark DynaGraft. It is comprised of demineralized bone matrix and poloxamer as a carrier material. Poloxamer is a reverse phase polymer which becomes more viscous with increasing temperature.

Nothing in the known prior art discloses or suggests the present invention. More specifically, nothing in the known prior art discloses or suggests a bone graft substitute composition including calcium sulfate, a mixing solution such as sterile water, and a plasticizing substance such as carboxymethylcellulose, and having an extended set time and sufficient robustness to withstand fluid impact with minimal erosion.

#### BRIEF SUMMARY OF THE INVENTION:

A basic concept of the present invention is to provide bone graft substitute composition having an extended set time and sufficient robustness to withstand fluid impact with minimal erosion for expanded clinical applications.

The bone graft substitute composition of the present invention comprises, in general, calcium sulfate; a mixing solution such as sterile water; and a plasticizing substance such as carboxymethylcellulose.

One object of the present invention is to provide a bone graft substitute composition that can be mixed into a paste and then loaded into a syringe and ejected for an extended period of time (e.g., more than ten minutes).

5 Another object of the present invention is to provide a bone graft substitute composition that can be mixed into a putty and then handled and formed into desired shapes for an extended period of time (e.g., more than ten minutes).

10

#### DETAILED DESCRIPTION OF THE INVENTION:

The bone graft substitute composition of the present invention comprises, in general, a quantity of calcium sulfate, a quantity of fluid (e.g., sterile water), and a  
15 quantity of a plasticizing substance (e.g., carboxymethylcellulose) which provides a resultant composition that is robust and has an extended set time. The extended set time of the resultant composition provides a useful working time of at least 10 minutes to  
20 allow sufficient time for a surgeon to properly apply the bone graft substitute composition, while the robustness of the resultant composition allows the implanted composition to withstand the typical pressure of body fluids, irrigation fluids and/or suctioning with minimal material  
25 erosion, disintegration or dissolution.

The bone graft substitute composition of the present invention may comprise a mixture of calcium sulfate; a mixing solution selected from the group consisting of sterile water, inorganic salts, and cationic surface  
30 active agents including sodium chloride, phosphate buffered saline, potassium chloride, sodium sulfate, potassium sulfate, EDTA, ammonium sulfate, ammonium acetate, and sodium acetate, etc.; and a plasticizing

substance selected from the group consisting of cellulose derivatives including sodium carboxymethylcellulose, methycellulose, hydroxypropyl methylcellulose, ethylcellulose, hydroxyethylcellulose and cellulose acetate butyrate, and higher molecular weight alcohols including glycerol and vinyl alcohols, etc. The bone graft substitute composition may include demineralized bone matrix. One formulation of the composition may be approximately 100 parts calcium sulfate by weight, 11.1 parts carboxymethylcellulose by weight, 185.2 parts water by weight, and 69.4 parts demineralized bone matrix by weight. Another formulation of the composition may be approximately 100 parts calcium sulfate by weight, 6.3 parts carboxymethylcellulose by weight, and 31 parts water by weight. Another formulation of the composition may be approximately 100 parts calcium sulfate by weight, 1.2 parts carboxymethylcellulose by weight, and 31 parts water by weight. Another formulation of the composition may be approximately 80-120 parts calcium sulfate by weight, 1-40 parts carboxymethylcellulose by weight, and 21-250 parts water by weight. The composition may include a bioactive agent selected from the group consisting of demineralized bone matrix, growth factors, hyaluronic acid, bone morphogenic proteins, bone autograft, and bone marrow, etc. The composition may include sodium bicarbonate. For example, the composition may include 0.1-2% sodium bicarbonate by weight for creating a porous structure in the resultant composition. Possible embodiments of the bone graft substitute composition of the present invention may include at least one additive selected from the group consisting of antiviral agent, antimicrobial agent, antibiotic agent, amino acid, peptide, vitamin, inorganic element, protein synthesis co-factor, hormone, endocrine

tissue, synthesizer, enzyme, polymer cell scaffolding agent with parenchymal cells, angiogenic drug, demineralized bone powder, collagen lattice, antigenic agent, cytoskeletal agent, mesenchymal stem cells, bone digester, antitumor agent, cellular attractant, fibronectin, growth hormone, cellular attachment agent, immunosuppressant, nucleic acid, surface active agent, hydroxyapatite, penetration enhancer, bone allograft, and chunks, shards, and/or pellets of calcium sulfate.

10

#### Preferred Embodiment 1:

An injectable bone graft substitute composition having the following preferred formulation: 100 parts by weight of medical grade calcium sulfate hemihydrate (MGCSH), 11.1 parts by weight of carboxymethylcellulose (CMC), 69.4 parts by weight of demineralized bone matrix (DBM), and 162 parts by weight of sterile water.

The preferred method for mixing this putty bone graft substitute composition comprises the following steps: (1) dry blend the powder components (i.e., the calcium sulfate hemihydrate, carboxymethylcellulose, and demineralized bone matrix); (2) add the sterile water; and (3) mix or stir all components for approximately 30 seconds to one minute or until the desired putty-like consistency is achieved.

The resultant injectable bone graft substitute composition has the following characteristic/criteria:

Handability – the resultant composition should:

- (a) be a single cohesive bolus; (b) be able to be handled and manipulated with minimal to no material transfer (sticking) to latex gloved hand; (c) be able to be handled without material crumbling or falling apart; and (d) exhibit minimal cracking or "tearing" with extreme

manipulation, e.g., hard squeezing;

Ejectability – the resultant composition should:

- (a) be able to be easily manipulated, e.g., rolled into a long cylinder or other suitable shape, so as to be  
5 manually placed into an appropriate injection apparatus, e.g., a syringe; and (b) be able to be ejected through a 1/8 inch (0.3175 centimeter) diameter orifice with relatively little pressure required; and

- Robustness – the resultant composition, after  
10 being placed or injected into or onto the desired location, should be able to withstand body fluids, reasonable irrigation fluids and/or suctioning with minimal material erosion, disintegration or dissolution.

15 Preferred Embodiment 2:

- A putty bone graft substitute composition having the following preferred formulation: 100 parts by weight of medical grade calcium sulfate hemihydrate (MGCSH), 6.3 parts by weight of carboxymethylcellulose (CMC), and 31  
20 parts by weight of sterile water.

- The preferred method for mixing this putty bone graft substitute composition comprises the following steps: (1) dry blend the powder components (i.e., the calcium sulfate hemihydrate, and carboxymethylcellulose); (2) add the  
25 sterile water; and (3) mix or stir all components for approximately 30 seconds to one minute or until the desired putty-like consistency is achieved.

The resultant putty bone graft substitute composition has the following characteristic/criteria:

- 30 Handability – the resultant composition should:  
(a) be a single cohesive bolus; (b) be able to be handled and manipulated with minimal to no material transfer (sticking) to latex gloved hand; (c) be able to be handled

without material crumbling or falling apart; and (d) exhibit minimal cracking or "tearing" with extreme manipulation, e.g., hard squeezing; and

Robustness - the resultant composition, after  
5 being placed or injected into or onto the desired location, should be able to withstand body fluids, reasonable irrigation fluids and/or suctioning with minimal material erosion, disintegration or dissolution.

10 Preferred Embodiment 3:

A paste bone graft substitute composition having the following preferred formulation: 100 parts by weight of medical grade calcium sulfate hemihydrate (MGCSH), 1.2 parts by weight of carboxymethylcellulose (CMC), and 31  
15 parts by weight of sterile water.

The preferred method for mixing this putty bone graft substitute composition comprises the following steps: (1) dry blend the powder components (i.e., the calcium sulfate hemihydrate, and carboxymethylcellulose); (2) add the  
20 sterile water; and (3) mix or stir all components for approximately 30 seconds to one minute or until the desired putty-like consistency is achieved.

The resultant paste bone graft substitute composition has the following characteristic/criteria:

25 Ejectability - the resultant composition should be able to be ejected through a 1/8 inch (0.3175 centimeter) diameter orifice with relatively little pressure required.

30 Preferred Embodiment 4:

A bone graft substitute composition having the following preferred formulation: approximately 80-120 parts medical grade calcium sulfate hemihydrate by weight;

approximately 21-250 parts sterile water by weight; and  
approximately 1-40 parts sodium carboxymethylcellulose by  
weight. This preferred formulation may include  
approximately 10-100 parts demineralized bone matrix by  
5 weight.

The preferred method for mixing this bone graft  
substitute composition comprises the following steps: (1)  
dry blend the powder components (i.e., the calcium sulfate  
hemihydrate, and sodium carboxymethylcellulose, and, if  
10 included, the demineralized bone matrix); (2) add the  
sterile water; and (3) mix or stir all components for  
approximately 30 seconds to one minute or until the  
desired consistency is achieved.

The resultant bone graft substitute composition has  
15 the following characteristic/criteria:

Handability - the resultant composition should:  
(a) be a single cohesive bolus; (b) be able to be handled  
and manipulated with minimal to no material transfer  
(sticking) to latex gloved hand; (c) be able to be handled  
20 without material crumbling or falling apart; and (d)  
exhibit minimal cracking or "tearing" with extreme  
manipulation, e.g., hard squeezing;

Ejectability - the resultant composition should:  
(a) be able to be easily manipulated, e.g., rolled into a  
25 long cylinder or other suitable shape, so as to be  
manually placed into an appropriate injection apparatus,  
e.g., a syringe; and (b) be able to be ejected through a  
1/8 inch (0.3175 centimeter) diameter orifice with  
relatively little pressure required; and

30 Robustness - the resultant composition, after  
being placed or injected into or onto the desired  
location, should be able to withstand body fluids,  
reasonable irrigation fluids and/or suctioning with

minimal material erosion, disintegration or dissolution.

#### Tests:

The majority of tests done to date on the bone graft  
5 substitute composition of the present invention basically  
consist of mixing a specific formulation and then  
assessing and recording the mixing, handling, consistency,  
and injectability properties of the resultant material.

#### 10 Formulation Tests:

Injectable Bone Graft Substitute Composition:  
Formulations with various types and amounts of  
carboxymethylcellulose and demineralized bone matrix have  
been tested. Specific examples include: (1)  
15 carboxymethylcellulose percentages of 1-10% by weight; (2)  
types of carboxymethylcellulose have included high  
viscosity, medium viscosity, and low viscosity from 3  
vendors (e.g., Aqualon® 7HF PH sodium  
carboxymethylcellulose from Hercules Incorporated,  
20 Hercules Plaza, 1313 North Market Street, Wilmington, DE  
19894-0001); (3) carboxymethylcellulose sterilized by  
gamma or electronic beam sterilization (medium and low  
doses); (4) demineralized bone matrix percentages up to  
65% by volume; (5) differently processed demineralized  
25 bone matrix, air dried and freeze dried; (6) demineralized  
bone matrix from two vendors (e.g., human freeze dried  
demineralized bone matrix from AlloSource, 8085 E. Harvard  
Ave., Denver, CO 80231); and (7) animal demineralized bone  
matrix, including bovine and canine.

30 For all these formulations, varying amounts of water,  
between 31-200 parts by weight, have been tested. The  
mixing, handling, consistency, and injectability  
properties were assessed and formulas chosen such that

they met the mixing, handability, ejectability, and robustness characteristics/criteria stated hereinabove.

Paste And Putty Bone Graft Substitute Composition:

These were the first tests done and included formulations with compositions having 100 parts by weight medical grade calcium sulfate hemihydrate, and between 1-10% by weight carboxymethylcellulose, and between 31-200 parts by weight water. As was the case with the injectable bone graft substitute composition, mixing, handability, consistency, injectability, and robustness properties were assessed for the different formulations. Specific tests have included: (1) varying the carboxymethylcellulose percentages from 0.25 % up to 10% by weight, (2) using inorganic salt solutions including 2% sodium chloride (NaCl) by weight, 2-4% sodium sulfate ( $\text{Na}_2\text{SO}_4$ ) by weight, and 2% potassium chloride (KCl) by weight.

As with the injectable bone graft substitute composition, varying amounts of water, 31-200 parts by weight, were used.

Example 1:

The osteoinductive properties of the injectable bone graft substitute composition have been studied using an athymic mouse-intramuscular implantation model. This animal model is widely accepted as the "gold standard" for assessing osteoinductive characteristics of bone graft materials. In this model, a given amount of material is surgically placed into a muscular site. After an implantation period of four weeks, the osteoinductive response is assessed using various analytical methods, including radiography, biochemical analysis (alkaline phosphatase levels and calcium content), and histomorphometry.

In this study, four athymic (nude) male mice (Harlan Sprague Dawley, Inc.) were used for each material group. Two muscle pouches were formed in the right and left gluteal muscles of each mouse and implanted with either:  
5 1) pellets which were manufactured using the composition given in Preferred Embodiment 1, or 2) twenty (20) mg of demineralized bone matrix which had been rehydrated with isotonic saline (0.9% NaCl). The pellets made from Preferred Embodiment 1 were 3.0 mm in diameter, 2.5 mm in  
10 height and 25 mg in weight.

After twenty-eight (28) days the animals were sacrificed and the materials explanted. The explants were analyzed for osteoinductive potential by assessing the alkaline phosphatase activity and for new bone growth by  
15 histomorphometric analysis of histologic sections.

Samples to be analyzed for alkaline phosphatase activity were minced, sonicated, and extracted with water saturated butanol. The extracts were assayed for protein content using a Pierce BCA Protein Assay Kit (Pierce  
20 Chemical Co.) and measuring the conversion of para-nitrophenylphosphate (pNPP) to para-nitrophenol (pNP) with time. The results were expressed as umole pNP formed/min/ug tissue protein.

Samples intended for histomorphometric analyses were  
25 prepared using standard histological procedures. The percent viable bone (new bone formation) was quantitated employing computer software (Adobe Photo Shop 3.0.4 and HNIH 1.61), in conjunction with a microscope equipped with a video camera. Data was reported as percent viable bone  
30 relative to the total cross-sectional area analyzed.

The alkaline phosphatase levels (umole pNP formed/min/ug tissue protein) and percent viable bone results for the groups of mice implanted with DBM only and

with injectable putty manufactured using the composition given in Preferred Embodiment 1 are shown in Table 1.

Table 1 - Osteoinductive Results

Alkaline Phosphatase Levels and Percent Viable Bone

Group	Alkaline Phosphatase Levels (umole pNP formed/min/ug tissue protein)	Percent Viable Bone (%)
DMB only	$2.1 \times 10^{-5} \pm 0.3 \times 10^{-5}$	$6.5 \pm 1.0\%$
Injectable Putty (Preferred Embodiment 1)	$3.0 \times 10^{-5} \pm 0.2 \times 10^{-5}$	$4.7 \pm 0.9\%$

5

Example 2:

A study was performed on canines to evaluate healing of bone defects using materials with the composition given in Preferred Embodiment 1. The DBM used in these compositions was fresh frozen canine DBM (Veterinarian Transplant Services, Seattle, WA). Two methods were used to produce the test materials. The first material group consisted of a blend of DBM, calcium sulfate, and CMC powder that was irradiated sterilized, while the second group mixed canine DBM with the calcium sulfate-CMC blend at the time of surgery.

In this canine animal model, large medullary cylindrical defects (13 mm diameter x 50 mm length) were created bilaterally in the proximal humeri by drilling axially through the greater tubercle. Six to 7 cc of test

20

material were injected into prepared cavities using a large-bore catheter-tip syringe. Left humeri received the premixed material that had been sterilized and the right humeri received the material mixed intraoperatively which  
5 utilized non-irradiated canine DBM. Radiographs of the humeri were obtained preoperative, immediately postoperative, and at 2, 3, and 6 weeks. Following euthanasia after 6 weeks, the explanted humeri were sectioned transversely, radiographed, and processed for  
10 plastic imbedded undecalcified histology. The histologic sections were stained with basic fuchsin and toluidine blue and examined by light microscopy.

Post-operative radiographs revealed all test materials to be well contained in the prepared cavities.  
15 Normal wound healing occurred and there were no postoperative infections. Serial clinical radiographs showed a progressive decrease in materials density with time. no difference was evident between the right and left sides.

20 Contact radiographs of the cut sections demonstrated no difference in pattern or density of bone filling the right and left defects, non-irradiated and irradiated canine DBM materials groups, respectively. Serial sections for all the dogs showed between 30-100% filling of the  
25 defect, with one dog showing almost complete filling for all sections.

Histologically, the nature of new bone formation and the amount of residual material were similar in the right and left defects. In the peripheral one-third of the  
30 defects, new bone was present at the margins and haversian surfaces of abundant DBM particles. Residual calcium sulfate was evident, incorporated within slender bone trabeculae, independent of DBM particles. New bone

formation in the central aspect of the defects was more variable, with some vascular fibrous tissue shown. No foreign body or inflammatory response was seen in any of the slides, indicating that the materials had extremely  
5 good biocompatibility.

Thus, materials with compositions given in Preferred Embodiment 1 were shown to be well tolerated by the bone and to heal a large medullary defect 30-100% at six weeks with viable new bone in a canine bone defect model.

10 Although the present invention has been described and illustrated with respect to preferred embodiments and preferred uses therefor, it is not to be so limited since modifications and changes can be made therein which are within the full intended scope of the invention.

## CLAIMS:

1. A bone graft substitute composition comprising:
  - (a) calcium sulfate;
  - 5 (b) a mixing solution selected from the group consisting of sterile water, inorganic salts, and cationic surface active agents including sodium chloride, phosphate buffered saline, potassium chloride, sodium sulfate, ammonium sulfate, ammonium acetate, and sodium acetate;
  - 10 and
  - (c) a plasticizing substance selected from the group consisting of cellulose derivatives including sodium carboxymethylcellulose, methycellulose, hydroxypropyl methylcellulose, ethylcellulose, hydroxethylcellulose and
  - 15 cellulose acetate butyrate, and higher molecular weight alcohols including glycerol and vinyl alcohols.
2. The bone graft substitute composition of claim 1 in which is included demineralized bone matrix.
- 20 3. The bone graft substitute composition of claim 2 in which said composition is approximately 40% demineralized bone matrix by dry weight.
- 25 4. The bone graft substitute composition of claim 2 in which said composition is approximately 100 parts calcium sulfate by weight, 11.1 parts carboxymethylcellulose by weight, 162 parts water by weight, and 69.4 parts demineralized bone matrix by
- 30 weight.
5. The bone graft substitute composition of claim 1 in which said composition is approximately 100 parts

calcium sulfate by weight, 6.3 parts  
carboxymethylcellulose by weight, and 31 parts water by  
weight.

5           6. The bone graft substitute composition of claim 1  
in which said composition is approximately 100 parts  
calcium sulfate by weight, 1.2 parts  
carboxymethylcellulose by weight, and 31 parts water by  
weight.

10

7. The bone graft substitute composition of claim 1  
in which said composition is approximately 80-120 parts  
calcium sulfate by weight, 1-40 parts  
carboxymethylcellulose by weight, and 21-250 parts water  
15 by weight.

8. The bone graft substitute composition of claim 1  
in which is included a bioactive agent selected from the  
group consisting of demineralized bone matrix, growth  
20 factors, hyaluronic acid, bone morphogenic proteins, bone  
autograft, therapeutic agents, analgesics, and bone  
marrow, bone allograft, and parenchymal and mesenchymal  
cells.

25           9. The bone graft substitute composition of claim 1  
in which is included sodium bicarbonate.

10. A bone graft substitute composition comprising:  
(a) calcium sulfate;  
30 (b) a mixing solution; and  
(c) a plasticizing substance for extending the set  
time of the resultant composition and for providing the  
resultant composition with sufficient robustness to

withstand fluid impact with minimal erosion.

11. A bone graft substitute composition comprising:

(a) approximately 80-120 parts medical grade calcium  
5 sulfate hemihydrate by weight;

(b) approximately 21-250 parts sterile water by  
weight; and

(c) approximately 1-40 parts sodium  
carboxymethylcellulose by weight.

10

12. The bone graft substitute of claim 11 in which is  
included approximately 10-100 parts demineralized bone  
matrix by weight.

## INTERNATIONAL SEARCH REPORT

International application No.  
PCT/US00/02780**A. CLASSIFICATION OF SUBJECT MATTER**

IPC(7) :A61K 33/06, 35/52

US CL :424/433, 423, 426, 549, 696

According to International Patent Classification (IPC) or to both national classification and IPC

**B. FIELDS SEARCHED**

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 424/433, 423, 426, 549, 696

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

BIOSIS, CAPLUS, MEDLINE, INPADOC, WEST

search terms: (calcium sulfate) and (demincralized bone matrix) and (?cellulose or glycerol)

**C. DOCUMENTS CONSIDERED TO BE RELEVANT**

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X -- Y	US 5,385,887 A (YIM et al.) 31 June 1995, see the entire document.	1, 8, 10, 11 ----- 2-7, 9, 12
X -- Y	WO 96/39203 A1 (BIOCOLL LABORATORIES, INC.) 12 December 1996, see the entire document.	1-2, 8-10 ----- 3-7, 11-12
Y	US 5,484,601 A (O'LEARY et al.) 16 January 1996, see the entire document.	1-12

☐ Further documents are listed in the continuation of Box C. ☐ See patent family annex.

* Special categories of cited documents:	*T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
*A* document defining the general state of the art which is not considered to be of particular relevance	*X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
*E* earlier document published on or after the international filing date	*Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
*L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	*G* document member of the same patent family
*O* document referring to an oral disclosure, use, exhibition or other means	
*P* document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search

23 JUNE 2000

Date of mailing of the international search report

14 AUG 2000

Name and mailing address of the ISA/US  
Commissioner of Patents and Trademarks  
Box PCT  
Washington, D.C. 20231

Facsimile No. (703) 305-3230

Authorized officer

JEAN C. WITZ

Telephone No. (703) 305-0196